

NIMA NH PC151

Polycarbonate
Ovation Polymers Inc.

Message:
Non-Hal FR-PC with High HDT, high impact and improved processability.

General Information			
Features	Flame Retardant		
	Good Processability		
	Halogen Free		
	High Impact Resistance		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	1580	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	52.0	MPa	
Break	46.0	MPa	
Tensile Elongation ³ (Break)	34	%	ASTM D638
Flexural Modulus ⁴ (50.0 mm Span)	1950	MPa	ASTM D790
Flexural Strength ⁵ (Break, 50.0 mm Span)	77.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	650	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	124	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	1.3 mm/min		
5.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

