

Rhelon G2050H-01A

Polyamide 66

RheTech, Inc.

Message:

Rhelon G2050H-01A is a Polyamide 66 (Nylon 66) product filled with 50% glass fiber. It can be processed by injection molding and is available in North America. Primary characteristic: heat stabilizer.

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.56	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.080 to 0.20	%	ASTM D955
Water Absorption (24 hr)	0.60	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	203	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	1.9	%	
Break	2.5	%	
Flexural Modulus	14500	MPa	ASTM D790
Flexural Strength	341	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	249	°C	
1.8 MPa, Unannealed	249	°C	
Peak Melting Temperature	254	°C	ASTM D789
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Suggested Max Moisture	0.20	%	
Suggested Max Regrind	25	%	
Rear Temperature	252 to 271	°C	
Middle Temperature	257 to 282	°C	
Front Temperature	263 to 285	°C	
Nozzle Temperature	263 to 285	°C	
Processing (Melt) Temp	263 to 282	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

