

Akulon® K222-KMV5 /A

Polyamide 6
DSM Engineering Plastics

Message:

Akulon® K222-KMV5 /A is a Polyamide 6 (Nylon 6) material filled with 25% mineral. It is available in Asia Pacific.
Important attributes of Akulon® K222-KMV5 /A are:
Flame Rated
Flame Retardant
Halogen Free

General Information				
Filler / Reinforcement		Mineral,25% Filler by Weight		
Additive		Flame Retardant		
Features		Flame Retardant		
		Halogen Free		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.38	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.82	--	%	
Flow	0.91	--	%	
Water Absorption				ISO 62
Saturation, 23°C	6.2	--	%	
Equilibrium, 23°C, 50% RH	1.8	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	6000	2500	MPa	ISO 527-2
Tensile Stress (Break)	65.0	35.0	MPa	ISO 527-2
Tensile Strain (Break)	2.5	30	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	2.0	--	kJ/m ²	
23°C	2.0	--	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	25	--	kJ/m ²	
23°C	29	--	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	205	--	°C	ISO 75-2/B

1.8 MPa, Unannealed	110	--	°C	ISO 75-2/A
Melting Temperature ¹	220	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	5.0E-5	--	cm/cm/°C	
Transverse	5.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	--	ohms·cm	IEC 60093
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.750 mm	V-2	--		
1.50 mm	V-2	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.750 mm	960	--	°C	
3.00 mm	960	--	°C	
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	225 to 235		°C	
Middle Temperature	230 to 240		°C	
Front Temperature	235 to 250		°C	
Nozzle Temperature	235 to 255		°C	
Processing (Melt) Temp	245 to 265		°C	
Mold Temperature	50.0 to 80.0		°C	
Injection Rate	Moderate-Fast			
Back Pressure	3.00 to 10.0		MPa	
Screw Compression Ratio	2.5:1.0			
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT