

CYCOLAC™ HMG94MD resin

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

Superior flow, injection molding ABS for medical applications. Good impact. For thin-wall applications. Biocompatible (ISO10993). FDA compliant. Gamma & EtO sterilizable.

General Information			
UL YellowCard	E45329-102071280		
Features	Radiation disinfection		
	Ethylene oxide disinfection		
	Impact resistance, good		
	Good liquidity		
	Biocompatibility		
	Compliance of Food Exposure		
Uses	Thin wall parts		
	Medical/nursing supplies		
Agency Ratings	FDA not rated		
	ISO 10993		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.04	g/cm ³	ASTM D792
--	1.06	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			
230°C/3.8 kg	12	g/10 min	ASTM D1238
220°C/5.0 kg	13	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.80	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2480	MPa	ASTM D638
--	2450	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	46.9	MPa	ASTM D638
Yield	40.0	MPa	ISO 527-2/5
Fracture ³	35.9	MPa	ASTM D638

Fracture	35.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	2.0	%	ASTM D638
Yield	2.0	%	ISO 527-2/5
Fracture ⁵	18	%	ASTM D638
Fracture	35	%	ISO 527-2/5
Flexural Modulus			
50.0mm span ⁶	2620	MPa	ASTM D790
-- ⁷	2500	MPa	ISO 178
Flexural Stress			
--	70.0	MPa	ISO 178
Yield, 50.0mm span ⁸	79.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	23	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	80	J/m	ASTM D256
23°C	240	J/m	ASTM D256
-30°C ¹⁰	7.0	kJ/m ²	ISO 180/1A
23°C ¹¹	16	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	21.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	93.0	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	77.0	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	80.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	98.0	°C	ASTM D1525, ISO 306/B50 11 ¹³
--	100	°C	ISO 306/B120
Linear thermal expansion coefficient			
Flow: -40 to 40°C	8.8E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	8.5E-5	cm/cm/°C	ISO 11359-2
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (240°C, 1000 sec ⁻¹)	1730	Pa · s	ISO 11443
Injection	Nominal Value	Unit	
Drying Temperature	82.2 - 87.8	°C	
Drying Time	2.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.10	%	
Suggested Shot Size	50 - 70	%	
Rear Temperature	188 - 199	°C	
Middle Temperature	199 - 210	°C	

Front Temperature	204 - 227	°C
Nozzle Temperature	204 - 246	°C
Processing (Melt) Temp	204 - 246	°C
Mold Temperature	48.9 - 71.1	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	30 - 60	rpm
Vent Depth	0.038 - 0.051	mm

NOTE

1.	5.0 mm/min
2.	Type 1, 5.0 mm/min
3.	Type 1, 5.0 mm/min
4.	Type 1, 5.0 mm/min
5.	Type 1, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT