

Sindustris ABS LAF416HT

Acrylonitrile Butadiene Styrene

Sincerity Australia Pty Ltd.

Message:

Sindustris ABS LAF416HT is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Asia Pacific for injection molding.

Important attributes of Sindustris ABS LAF416HT are:

Flame Rated

Flame Retardant

Heat Resistant

Typical applications include:

Housings

Electrical/Electronic Applications

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	High Heat Resistance		
Uses	Electrical Housing		
	Electrical/Electronic Applications		
	Housings		
	Television Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (3.20 mm)	1960	MPa	ASTM D638
Tensile Strength ² (Yield, 3.20 mm)	39.2	MPa	ASTM D638
Tensile Elongation ³			ASTM D638
Yield, 3.20 mm	5.0	%	
Break, 3.20 mm	20	%	
Flexural Modulus ⁴ (6.40 mm)	2260	MPa	ASTM D790
Flexural Strength ⁵ (6.40 mm)	66.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	59	J/m	

-30°C, 6.40 mm	39	J/m	
23°C, 3.20 mm	180	J/m	
23°C, 6.40 mm	88	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	102	°C	
1.8 MPa, Unannealed, 6.40 mm	91.0	°C	
Vicat Softening Temperature	100	°C	ASTM D1525 ⁶
RTI Elec	85.0	°C	UL 746
RTI Imp	85.0	°C	UL 746
RTI Str	85.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	V-0		
	V-0		
2.00 mm	5VA		
	V-0		
3.00 mm	5VA		
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.010	%	
Rear Temperature	180 to 200	°C	
Middle Temperature	190 to 210	°C	
Front Temperature	200 to 220	°C	
Nozzle Temperature	200 to 230	°C	
Processing (Melt) Temp	200 to 230	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	0.490 to 0.981	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	1.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	15 mm/min		
5.	15 mm/min		
6.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

