

ALTECH® PP-H A 1000/249 FR

Polypropylene Homopolymer

ALBIS PLASTIC GmbH

Message:

ALTECH® PP-H A 1000/249 FR is a Polypropylene Homopolymer (PP Homopolymer) product. It is available in Asia Pacific, Europe, or North America. Characteristics include:
Flame Rated
REACH Compliant
RoHS Compliant
Flame Retardant
High Flow

General Information			
UL YellowCard	E80168-626889		
Additive	Flame Retardant		
	Metal Deactivator		
Features	Flame Retardant		
	High Flow		
	Homopolymer		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	30.0	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-2
Tensile Stress (Break)	40.0	MPa	ISO 527-2
Tensile Strain (Break)	14	%	ISO 527-2
Flexural Stress	50.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.2	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	60	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	73.0	°C	ISO 75-2/A
Vicat Softening Temperature	100	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (0.750 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature			

Circulation Dryer	80.0 to 120	°C
Desiccant Dryer	80.0 to 120	°C
Drying Time		
Circulation Dryer	2.0 to 4.0	hr
Desiccant Dryer	2.0 to 3.0	hr
Processing (Melt) Temp	200 to 270	°C
Mold Temperature	20.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

