

Apec® 1897

Polycarbonate

Covestro - Polycarbonates

Message:

MVR (330°C/2.16kg) 18 cm³/10 min; easy release; UV stabilized; 'softening temperature (VST/B 120)=182°C; injection molding - melt temperature 330 - 340°C; Lamp covers; Headlamp lenses

General Information			
UL YellowCard	E41613-508369		
Additive	UV Stabilizer		
Features	Good Flow		
	Good Mold Release		
Uses	Lenses		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.15	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (330°C/2.16 kg)	19	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (330°C/2.16 kg)	18.0	cm ³ /10min	ISO 1133
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.85	%	
Flow : 2.00 mm	0.85	%	
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.12	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	127	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2450	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	74.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	6.6	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	> 50	%	ISO 527-2/50
Flexural Modulus ² (23°C)	2450	MPa	ISO 178
Flexural Stress ³ (23°C)	108	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	172	°C	ISO 75-2/B
1.8 MPa, Unannealed	157	°C	ISO 75-2/A
Vicat Softening Temperature	182	°C	ISO 306/B120
CLTE			ISO 11359-2
Flow : 23 to 55°C	6.5E-5	cm/cm/°C	
Transverse : 23 to 55°C	6.5E-5	cm/cm/°C	
RTI Elec	150	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	150	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+17	ohms·cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	35	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	2.90		
23°C, 1 MHz	2.80		
Dissipation Factor			IEC 60250
23°C, 100 Hz	1.0E-3		
23°C, 1 MHz	9.0E-3		
Comparative Tracking Index			IEC 60112
Solution A	250	V	
Solution B	100	V	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Glow Wire Flammability Index	850	°C	IEC 60695-2-12
Oxygen Index ⁴	26	%	ISO 4589-2
Optical	Nominal Value	Unit	Test Method
Refractive Index ⁵	1.573		ISO 489
Transmittance (1000 μm)	89.0	%	ISO 13468-2
Additional Information	Nominal Value		Test Method
Electrolytical Corrosion (23°C)	A1		IEC 60426
NOTE			
1.	60x60x2 mm		
2.	2.0 mm/min		
3.	2.0 mm/min		
4.	Procedure A		
5.	Method A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT