

Silopren® LSR 3286/70

Silicone Rubber, LSR

Momentive Performance Materials Inc.

Message:

Silopren LSR 3286/70 is a two-component liquid silicone rubber for injection molding processes. This material is an excellent candidate to consider for the manufacture of elastomeric articles requiring self-lubricating properties. The self-lubricating effect is achieved by a fluid which exudes out of the vulcanizate over an extended period of time. It typically starts between a few hours and one day after vulcanization. Silopren LSR 3286/70 liquid silicone rubber shows a low compression set after vulcanization without post-curing.

Key Features and Benefits

Vulcanizates consisting of Silopren LSR 3286/70 liquid silicone rubber are typically distinguished by the following properties:

low compression set without post-cure

self-lubricating properties

low viscosity

fast cure

high thermal stability

outstanding resistance to aging

easy to color

Potential Applications

Because of the outstanding properties Silopren LSR 3286/70 liquid silicone rubber is an excellent candidate to consider for use in wire harness applications for the following elastomeric articles:

cable seals

grommets

gaskets

plug seals

General Information			
Features	Fast Cure		
	Fast Molding Cycle		
	Good Colorability		
	Good Mold Release		
	Good Thermal Stability		
	Low Compression Set		
	Low Viscosity		
	Self Lubricating		
Uses	Gaskets		
	Grommets		
	Seals		
Forms	Liquid		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	DIN 53479
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	69		DIN 53505
Elastomers	Nominal Value	Unit	Test Method

Tensile Strength	10.5	MPa	DIN 53504
Tensile Elongation (Break)	420	%	DIN 53504
Tear Strength ¹	37.0	kN/m	ASTM D624
Compression Set (175°C, 22 hr)	20	%	ISO 815
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Part A	Mix Ratio by Weight: 1.0		
Part B	Mix Ratio by Weight: 1.0		
Shelf Life (< 27°C)	77	wk	
Additional Information	Nominal Value	Unit	Test Method
Vulcanization (175°C)	10.0	min	
Fluid Content			
-- ²	2.0	%	
-- ³	2.0	%	
Uncured Properties	Nominal Value	Unit	Test Method
Color			
-- ⁴	Translucent		
-- ⁵	Translucent		
Viscosity			DIN 53018
20°C ⁶	890	Pa·s	
20°C ⁷	920	Pa·s	
Pot Life (20°C)	4300	min	
NOTE			
1.	Die B		
2.	Part B		
3.	Part A		
4.	Part B		
5.	Part A		
6.	Part B		
7.	Part A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT