Baytec® MP-080

Polyurethane (Polyether, MDI)

Covestro - PUR

Message:

Baytec MP-080 diphenylmethane diisocyanate (MDI)-terminated polyether prepolymer is based on polypropylene ether glycol (PPG).

General Information			
Forms	Liquid		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	4.32	MPa	ASTM D412
300% strain	7.43	MPa	ASTM D412
Tensile Strength (Break)	9.93	MPa	ASTM D412
Tensile Elongation (Break)	470	%	ASTM D412
Additional Information			

Appearance: Yellow viscous liquidNCO: 7.8 to 8.2 wt%Viscosity at 25°C: 2500 mPa-sSpecific Gravity at 25°C: 1.08Flash Point, PMCC: 200°CDensity at 25°C: 9.05 lb/gal

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

