

RONFALIN® FFA59

Acrylonitrile Butadiene Styrene

A. Schulman Europe

Message:

RONFALIN® FFA59 is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of RONFALIN® FFA59 are:

Flame Rated

RoHS Compliant

Antistatic

High Flow

Typical application of RONFALIN® FFA59: Appliances

General Information			
Additive	Antistatic		
Features	Antistatic		
	High Flow		
Uses	Appliance Components		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	43	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.60	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	96.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	45.0	MPa	ISO 527-2/50
Flexural Modulus	2350	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	18	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	95.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	89.0	°C	ISO 75-2/A
Vicat Softening Temperature	95.0	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Electric Strength	> 25	kV/mm	IEC 60243-1
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

