

POLYREX® PH-88S

High Impact Polystyrene

CHI MEI CORPORATION

Message:

POLYREX® PH-88S is a High Impact Polystyrene product. It can be processed by extrusion and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E56070-245791		
RoHS Compliance	RoHS Compliant		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	2.6	g/10 min	
220°C/10.0 kg	8.5	g/10 min	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	50		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.00 mm)	25.5	MPa	ASTM D638
Tensile Elongation ² (Break, 3.00 mm)	55	%	ASTM D638
Flexural Modulus ³ (6.00 mm)	1860	MPa	ASTM D790
Flexural Strength ⁴ (6.00 mm)	35.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
23°C, 3.00 mm	150	J/m	
23°C, 6.00 mm	110	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	80.0	°C	
1.8 MPa, Annealed	94.0	°C	
Vicat Softening Temperature	100	°C	ASTM D1525 ⁵
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 3.0	hr	
Cylinder Zone 1 Temp.	180 to 200	°C	

Cylinder Zone 3 Temp.	200 to 220	°C
Cylinder Zone 5 Temp.	200 to 230	°C
Die Temperature	200 to 230	°C

NOTE		
1.	6.0 mm/min	
2.	6.0 mm/min	
3.	2.8 mm/min	
4.	2.8 mm/min	
5.	Rate A (50°C/h)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT