

SABIC® HDPE B1054

High Density Polyethylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® HDPE B1054 is a material with a specific molecular weight distribution, typically used for blow moulding of light weight and UN certified cans from 2 until 20 liters.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

General Information			
Features	High density		
Uses	Container		
Processing Method	Blow molding		
Physical	Nominal Value	Unit	Test Method
Density	0.954	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/21.6 kg	9.5	g/10 min	ISO 1133
190°C/5.0 kg	0.43	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance (10% Igepal CO-630, Compression Molded, F50)	> 1000	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	61		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (2.00 mm, Compression Molded)	1250	MPa	ISO 527-2/1BA/50
Tensile Stress			ISO 527-2/1BA/50
Yield, 2.00mm, molded	26.0	MPa	ISO 527-2/1BA/50
Fracture, 2.00mm, molded	39.0	MPa	ISO 527-2/1BA/50
Tensile Strain			ISO 527-2/1BA/50
Yield, 2.00mm, molded	13	%	ISO 527-2/1BA/50
Fracture, 2.00mm, molded	> 1000	%	ISO 527-2/1BA/50
Flexural Modulus (2.00 mm, Compression Molded)	1250	MPa	ISO 178
Flexural Stress (2.00 mm, Compression Molded)	27.0	MPa	ISO 178
ESCR (Strain Hardening) - Gp	27.0	MPa	ISO 18488
Enthalpy Change	195	J/g	ISO 11357-3
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/A
-30°C, molded	12	kJ/m ²	ISO 180/A
23°C, molded	20	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (0.45 MPa, Unannealed)	78.0	°C	ISO 75-2/B
Vicat Softening Temperature	129	°C	ISO 306/A
Melting Temperature (DSC)	132	°C	ISO 11357-3

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

