

Alpha PVC 7761 NATURAL

Polyvinyl Chloride

AlphaGary

Message:

AUTOMOTIVE WINDOW SEAL RECOMMENDED FOR GMP.PVC.088.

General Information			
Uses	Automotive Applications		
RoHS Compliance	Contact Manufacturer		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23 to 1.27	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	62 to 68		
Shore A, 15 sec	47 to 53		
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (1.91 mm)	8.14	MPa	ASTM D412
Tensile Elongation (Break, 1.91 mm)	400	%	ASTM D412
Compression Set (70°C, 22 hr)	35	%	ASTM D395B
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-33.0	°C	ASTM D746

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT