

Cevian® SEHG20

Acrylonitrile Butadiene Styrene

PlastxWorld Inc.

Message:

Cevian® SEHG20 is an Acrylonitrile Butadiene Styrene (ABS) product filled with 20% glass fiber. It can be processed by injection molding and is available in North America. Applications of Cevian® SEHG20 include electrical/electronic applications and business/office goods.

Characteristics include:

- Flame Rated
- Good Dimensional Stability
- Good Processability
- Heat Resistant
- Rigid

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Dimensional Stability		
	Good Moldability		
	High Heat Resistance		
	High Rigidity		
Uses	Business Equipment		
	Computer Components		
	Electrical Parts		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	62.1	MPa	ASTM D638
Flexural Modulus	5860	MPa	ASTM D790
Flexural Strength (Yield)	89.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	108	°C	ASTM D648

CLTE - Flow	5.3E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.1E+16	ohms·cm	ASTM D257
Dielectric Strength	27	kV/mm	ASTM D149
Arc Resistance (3.18 mm)	63.0	sec	ASTM D495
Comparative Tracking Index (CTI) (3.18 mm)	525	V	UL 746
High Voltage Arc Tracking Rate (HVTR) (3.18 mm)	152	mm/min	UL 746
Hot-wire Ignition (HWI)			UL 746
1.59 mm	33	sec	
3.18 mm	120	sec	
6.35 mm	120	sec	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	220 to 240	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Pressure	49.0 to 97.9	MPa	
Screw Speed	40 to 60	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

