

Tekumid 6 SC/GK 30

Polyamide 6
TEKUMA Kunststoff GmbH

Message:
Tekumid 6 SC/GK 30 is a Polyamide 6 (Nylon 6) material filled with 30% glass bead. It is available in Europe.

General Information			
Filler / Reinforcement	Glass Bead,30% Filler by Weight		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792
Ash Content	30	%	
Moisture	< 150	kg/m ³	ISO 960
Heat Resistance	76	°C	ASTM D648
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	2730	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	60	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	195	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT