

Clariant Nylon 6/6 6601-L BK-09

Polyamide 66
Clariant Corporation

Message:

Clariant Nylon 6/6 6601-L BK-09 is a Polyamide 66 (Nylon 66) material. It is available in North America for injection molding. Primary attribute of Clariant Nylon 6/6 6601-L BK-09: Lubricated.

General Information			
UL YellowCard	E103015-218184		
Additive	Lubricant		
Features	General Purpose		
	Lubricated		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.2 to 1.7	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	75.8	MPa	ASTM D638
Tensile Elongation (Break)	40	%	ASTM D638
Flexural Modulus	2760	MPa	ASTM D790
Flexural Strength	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	229	°C	
1.8 MPa, Unannealed	87.8	°C	
Melting Temperature	257	°C	
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Suggested Max Regrind	25	%	
Rear Temperature	249 to 266	°C	
Middle Temperature	271 to 288	°C	
Front Temperature	282 to 293	°C	
Nozzle Temperature	266 to 288	°C	
Mold Temperature	54.4 to 93.3	°C	
Injection Pressure	34.5 to 103	MPa	
Back Pressure	0.00 to 5.52	MPa	

Screw Speed

30 to 90

rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT