

NORYL GTX™ GTX985 resin

Polyphenylene Ether + PS + Nylon

SABIC Innovative Plastics Europe

Message:

NORYL GTX985 is a 18% mineral filled material. This material combines high stiffness and excellent temperature resistance with conductivity for electrostatic painting.

General Information			
Filler / Reinforcement	Mineral, 18% Filler by Weight		
Features	Conductive		
	High Heat Resistance		
	High Stiffness		
	Paintable		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (280°C/5.0 kg)	16	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (280°C/5.0 kg)	15.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	1.1	%	Internal Method
Water Absorption (Equilibrium, 23°C, 50% RH)	1.1	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	60.0	MPa	ASTM D638
--	4400	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	65.0	MPa	ASTM D638
Yield	65.0	MPa	ISO 527-2/5
Break ³	60.0	MPa	ASTM D638
Break	60.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	4.0	%	ASTM D638
Yield	4.0	%	ISO 527-2/5
Break ⁵	7.0	%	ASTM D638
Break	7.0	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	4200	MPa	ASTM D790
-- ⁷	4350	MPa	ISO 178

Flexural Stress			
--	105	MPa	ISO 178
Yield, 50.0 mm Span ⁸	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	4.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	40	J/m	ASTM D256
23°C	45	J/m	ASTM D256
-30°C ¹⁰	4.0	kJ/m ²	ISO 180/1A
23°C ¹¹	4.5	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹²			ISO 180/1U
-30°C	55	kJ/m ²	
23°C	60	kJ/m ²	
Instrumented Dart Impact (23°C, Total Energy)	10.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	200	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹³	205	°C	ISO 75-2/Bf
Vicat Softening Temperature			
--	195	°C	ASTM D1525, ISO 306/B50 ¹¹ ¹⁴
--	200	°C	ISO 306/B120
CLTE			ISO 11359-2
Flow : 23 to 60°C	6.0E-5	cm/cm/°C	
Transverse : 23 to 60°C	6.5E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+3 to 1.0E+4	ohms · cm	Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	2.0 to 3.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	80.0 to 100	°C	
Rear Temperature	260 to 280	°C	
Middle Temperature	280 to 300	°C	
Front Temperature	300 to 320	°C	
Nozzle Temperature	280 to 300	°C	
Processing (Melt) Temp	300 to 320	°C	
Mold Temperature	100 to 120	°C	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		

4.	Type I, 5.0 mm/min
5.	Type I, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*3
13.	80*10*4 mm
14.	Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

