

Sylvin 9604-90 Black

Polyvinyl Chloride
Sylvin Technologies Incorporated

Message:

Sylvin 9604-90 Black, Blue And Red 6292 Are Vinyl Compounds Formulated For Electrical Molding Applications. This Compound Has A Underwriters Laboratories Listing As A Recognized Component And A Operating Temperature Of -40°C To 85°C.

General Information			
UL YellowCard	E86418-252048		
Uses	Electrical Parts		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	17.9	MPa	ASTM D638
Tensile Elongation (Break)	280	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	96.3	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Melting Temperature	171 to 182	°C	
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT