

ENVIROPLAS® ENV00-NC670

Acrylonitrile Butadiene Styrene

ENVIROPLAS®, Inc.

Message:

Injection Molding Grade, 5% Fiberglass Reinforced, RoHS Compliant

NC670 = To Be Assigned 5 Digit Number Indicating Natural, Black, or Custom Color.

The ENV00 Series Products Are Available With Mold Release and/or UV Stabilizer.

General Information			
Filler / Reinforcement	Glass Fiber,5.0% Filler by Weight		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
220°C/10.0 kg	7.8	g/10 min	
230°C/3.8 kg	5.0	g/10 min	
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Ash Content	5.0	%	ASTM D5630
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	44.1	MPa	ASTM D638
Flexural Modulus	2900	MPa	ASTM D790
Flexural Strength	62.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	91	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	94.4	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (3.00 mm)	HB		Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	85.0	°C	
Drying Time	3.0 to 5.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	232 to 260	°C	
Middle Temperature	232 to 260	°C	

Front Temperature	232 to 260	°C
Nozzle Temperature	232 to 260	°C
Mold Temperature	48.9 to 65.6	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.689 to 2.07	MPa
Screw Speed	30 to 60	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

