

LNP™ VERTON™ RV00CESS compound

Polyamide 66

SABIC Innovative Plastics

Message:

LNP VERTON* RV00CESS is a compound based on Nylon 66 resin containing 60% Long Glass Fiber. Added features of this material include: Easy Molding, Heat Stabilized, Structural.

Also known as: LNP* VERTON* Compound RF-700-12 EM HS

Product reorder name: RV00CESS

General Information			
UL YellowCard	E121562-101344708		
Filler / Reinforcement	Long Glass Fiber,60% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Moldability		
	Heat Stabilized		
Uses	Structural Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.71	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.20	%	ASTM D955, ISO 294-4
Across Flow : 24 hr	0.40	%	ASTM D955
Across Flow : 24 hr	0.41	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.44	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	19700	MPa	ASTM D638
--	23300	MPa	ISO 527-2/1
Tensile Strength			
Break	270	MPa	ASTM D638
Break	261	MPa	ISO 527-2
Tensile Elongation (Break)	1.6	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	18000	MPa	ASTM D790
--	18900	MPa	ISO 178
Flexural Strength			
--	430	MPa	ASTM D790
--	433	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			

23°C	410	J/m	ASTM D256
-40°C ²	43	kJ/m ²	ISO 180/1A
23°C ³	54	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁴ (23°C)	100	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	18.0	J	ASTM D3763
--	18.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 64.0 mm Span ⁵	252	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	247	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁶	252	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	1.8E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	1.7E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	5.4E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	5.3E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	282 to 293	°C	
Middle Temperature	288 to 299	°C	
Front Temperature	288 to 299	°C	
Processing (Melt) Temp	288 to 304	°C	
Mold Temperature	93.3 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4		
5.	80*10*4 mm		
6.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

