

Greenflex® MH 40

Ethylene Vinyl Acetate Copolymer

Versalis S.p.A.

Message:

Greenflex MH 40 is an ethylene vinyl acetate copolymer (EVA) for injection moulding and extrusion.

Items produced with Greenflex MH 40 show high elasticity and good mechanical properties.

Main Application

Greenflex MH 40 is recommended for the production flexible items, foamed and crosslinked sheets for shoes.

General Information			
Features	Copolymer		
	Crosslinkable		
	Foamable		
	Food Contact Acceptable		
	Good Flexibility		
	High Elasticity		
Uses	Foam		
	Footwear		
	Sheet		
Agency Ratings	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.938	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.8	g/10 min	ISO 1133
Vinyl Acetate Content	17.0	wt%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, Injection Molded	89		
Shore D, Injection Molded	36		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, Injection Molded)	5.60	MPa	ISO 527-2
Flexural Modulus (Injection Molded)	40.0	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -80.0	°C	ASTM D746
Vicat Softening Temperature	62.0	°C	ISO 306/A

Melting Temperature	88.0	°C	Internal Method
Injection	Nominal Value	Unit	
Processing (Melt) Temp	140 to 200	°C	
Mold Temperature	10.0 to 30.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

