

SUMIPEX® MH_EXTRA

Polymethyl Methacrylate Acrylic

Sumitomo Chemical Co., Ltd.

Message:

SUMIPEX® MH_EXTRA is a Polymethyl Methacrylate Acrylic material. It is available in Asia Pacific, Europe, or North America.

Important attributes of SUMIPEX® MH_EXTRA are:

Flame Rated

Chemical Resistant

Good Weather Resistance

Heat Resistant

Impact Resistant

Typical application of SUMIPEX® MH_EXTRA: Automotive

General Information			
Features	Good Chemical Resistance		
	Good Drawdown		
	Good Impact Resistance		
	Good Weather Resistance		
	High Heat Resistance		
UL File Number	E54705B		
Appearance	Clear/Transparent		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.19	g/cm ³	JIS K7112
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	2.0	g/10 min	JIS K7210
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	100		JIS K7202
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	76.0	MPa	JIS K7113
Tensile Elongation (Break)	9.0	%	JIS K7113
Flexural Modulus	3200	MPa	JIS K7203
Flexural Strength	120	MPa	JIS K7203
Flexural Rigidity	6.0	%	JIS K7203
Die Swell Comparison	1.50		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.7	kJ/m ²	JIS K7110
Charpy Unnotched Impact Strength	1.4	kJ/m ²	JIS K7110
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ² (1.8 MPa, Annealed)	100	°C	JIS K7207
Vicat Softening Temperature	108	°C	JIS K7206
Flammability	Nominal Value		Test Method

Flame Rating (1.59 mm, All Colors)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		JIS K7105
Transmittance ³	93.0	%	JIS K7105
Haze	< 0.50	%	JIS K7105
NOTE			
1.	Method A		
2.	VST 25±3, 4 hrs		
3.	Method A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

