

Retpol® 200 GF HS

Polypropylene Homopolymer

PolyPacific Pty. Ltd.

Message:

Extron 200 GF HS is a 20% glass fibre reinforced homopolymer polypropylene compound. It is a low flow injection moulding grade developed for rigid components requiring high heat deflection temperatures and low mould shrinkages. It is stabilized to meet automotive heat ageing requirements of 500hrs at 150°C.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	Homopolymer		
	Low Flow		
	Low Shrinkage		
Uses	Automotive Applications		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	0.20 to 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 3.00 mm)	111		ASTM D785
Durometer Hardness			ASTM D2240
Shore D, 3.00 mm	79		
Shore D, 15 sec, 3.00 mm	72		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.00 mm)	59.0	MPa	ASTM D638
Tensile Elongation ² (Break, 3.00 mm)	3.0	%	ASTM D638
Flexural Modulus (3.00 mm)	3900	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.00 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.00 mm)	270	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.00 mm	150	°C	
1.8 MPa, Unannealed, 3.00 mm	130	°C	
CLTE - Flow (-30 to 30°C, 3.00 mm)	4.0E-5	cm/cm/°C	ASTM D696

Injection	Nominal Value	Unit
Drying Temperature	100 to 120	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Regrind	10	%
Processing (Melt) Temp	200 to 260	°C
Mold Temperature	20.0 to 60.0	°C
Injection Rate	Moderate	
NOTE		
1.	50 mm/min	
2.	50 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT