

# NILAMID® A3 H GF15 TP07S

Polyamide 66

Nilit Plastics

## Message:

NILAMID® A3 H GF15 TP07S is a Polyamide 66 (Nylon 66) compound, 15% glass fiber reinforced, low wear and friction, heat stabilized.

This compound is intended for injection molding.

NILAMID® A3 H GF15 TP07S is primarily designed for the Industrial and Consumer industry. It is also suitable for Electrical and Electronic or Automotive applications.

| General Information              |                                    |                   |             |
|----------------------------------|------------------------------------|-------------------|-------------|
| Filler / Reinforcement           | Glass Fiber,15% Filler by Weight   |                   |             |
| Additive                         | Heat Stabilizer                    |                   |             |
| Features                         | Good Wear Resistance               |                   |             |
|                                  | Heat Stabilized                    |                   |             |
|                                  | Low Friction                       |                   |             |
| Uses                             | Automotive Applications            |                   |             |
|                                  | Consumer Applications              |                   |             |
|                                  | Electrical/Electronic Applications |                   |             |
|                                  | Industrial Applications            |                   |             |
| Processing Method                | Injection Molding                  |                   |             |
| Physical                         | Nominal Value                      | Unit              | Test Method |
| Density (23°C)                   | 1.20                               | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage                |                                    |                   | ISO 294-4   |
| Across Flow : 23°C               | 1.0                                | %                 |             |
| Flow : 23°C                      | 0.70                               | %                 |             |
| Water Absorption                 |                                    |                   | ISO 62      |
| 23°C, 24 hr                      | 1.2                                | %                 |             |
| Saturation, 23°C                 | 6.5                                | %                 |             |
| Mechanical                       | Nominal Value                      | Unit              | Test Method |
| Tensile Modulus (23°C)           | 4500                               | MPa               | ISO 527-2   |
| Tensile Stress (Yield, 23°C)     | 95.0                               | MPa               | ISO 527-2   |
| Tensile Strain (Yield, 23°C)     | 3.5                                | %                 | ISO 527-2   |
| Impact                           | Nominal Value                      | Unit              | Test Method |
| Charpy Notched Impact Strength   |                                    |                   | ISO 179/1eA |
| -30°C                            | 3.5                                | kJ/m <sup>2</sup> |             |
| 23°C                             | 4.0                                | kJ/m <sup>2</sup> |             |
| Charpy Unnotched Impact Strength |                                    |                   | ISO 179/1eU |
| 23°C                             | 40                                 | kJ/m <sup>2</sup> |             |
| 30°C                             | 30                                 | kJ/m <sup>2</sup> |             |

| Notched Izod Impact Strength                     |               |                   | ISO 180/A      |
|--------------------------------------------------|---------------|-------------------|----------------|
| -30°C                                            | 4.5           | kJ/m <sup>2</sup> |                |
| 23°C                                             | 5.0           | kJ/m <sup>2</sup> |                |
| Thermal                                          | Nominal Value | Unit              | Test Method    |
| Heat Deflection Temperature                      |               |                   |                |
| 0.45 MPa, Unannealed                             | 240           | °C                | ISO 75-2/B     |
| 1.8 MPa, Unannealed                              | 225           | °C                | ISO 75-2/A     |
| Continuous Use Temperature <sup>1</sup>          | 100           | °C                | IEC 60216      |
| Ball Pressure Test                               |               |                   | IEC 60695-10-2 |
| 125°C                                            | Pass          |                   |                |
| 165°C                                            | Pass          |                   |                |
| Electrical                                       | Nominal Value | Unit              | Test Method    |
| Surface Resistivity <sup>2</sup>                 | 1.0E+13       | ohms              | IEC 60093      |
| Volume Resistivity (23°C)                        | 1.0E+15       | ohms·cm           | IEC 60093      |
| Electric Strength (2.00 mm)                      | 22            | kV/mm             | IEC 60243-1    |
| Comparative Tracking Index (3.20 mm, Solution A) | 500           | V                 | IEC 60112      |
| Flammability                                     | Nominal Value | Unit              | Test Method    |
| Flame Rating                                     |               |                   | UL 94          |
| 0.800 mm                                         | HB            |                   |                |
| 1.60 mm                                          | HB            |                   |                |
| 3.20 mm                                          | HB            |                   |                |
| Glow Wire Flammability Index                     |               |                   | IEC 60695-2-12 |
| 0.800 mm                                         | 650           | °C                |                |
| 3.20 mm                                          | 650           | °C                |                |
| Glow Wire Ignition Temperature                   |               |                   | IEC 60695-2-13 |
| 0.800 mm                                         | 675           | °C                |                |
| 3.20 mm                                          | 675           | °C                |                |
| Oxygen Index                                     | 24            | %                 | ISO 4589-2     |
| NOTE                                             |               |                   |                |
| 1.                                               | 20000 hr      |                   |                |
| 2.                                               | 23°C          |                   |                |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT