

PENTAMID B GV35 H RC schwarz

Polyamide 6
PENTAC Polymer GmbH

Message:
Normal viscosity, heat stabilised polyamide 6, 35% glass fiber reinforced

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 35% filler by weight		
Additive		heat stabilizer		
Recycled Content		Yes		
Features		Thermal Stability		
Uses		Shell		
Agency Ratings		EC 1907/2006 (REACH)		
Appearance		Black		
Forms		Particle		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.39	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturated, 23°C	6.2	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.0	--	%	ISO 62
Viscosity Number	130	--	cm ³ /g	ISO 307
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 961/30)	230	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10000	6300	MPa	ISO 527-2/1
Tensile Stress (Break)	165	100	MPa	ISO 527-2
Tensile Strain (Break)	3.0	6.5	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	18	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	75	90	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	210	--	°C	ISO 75-2/B
1.8 MPa, not annealed	195	--	°C	ISO 75-2/A
Melting Temperature (DSC)	222	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method

Dielectric Strength (1.00 mm)	70	--	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	3.80	--		IEC 60250
Comparative Tracking Index	400	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (3.20 mm)	HB	--		UL 94

Additional Information

干燥
ISO Description: PA6, MHRC, 14-100, GF35The value listed as Melting Point, ISO 3146, was tested in accordance with ISO 11357.

调节后的
ISO Description: PA6, MHRC, 14-100, GF35

Injection	Dry	Unit
Drying Temperature	80.0	°C
Drying Time	3.0	hr
Suggested Max Moisture	0.090	%
Suggested Max Regrind	20	%
Rear Temperature	260 - 285	°C
Middle Temperature	275 - 290	°C
Front Temperature	275 - 285	°C
Processing (Melt) Temp	280	°C
Mold Temperature	80.0	°C
Injection Pressure	75.0	MPa
Holding Pressure	45.0	MPa
Screw L/D Ratio	20.0:1.0	
Screw Compression Ratio	2.2:1.0 to 2.8:1.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT