

# PEARLSTICK® 46-10/16

Thermoplastic Polyurethane Elastomer (Polyester)

Lubrizol Advanced Materials, Inc.

## Message:

Pearlstick® 46-10/16 is an elastic, linear, aromatic polyurethane, supplied in form of white spherical granules with a very high crystallization rate and a high thermoplasticity level.

### APPLICATIONS:

Pearlstick® 46-10/16 is used for the production of adhesives for plasticized PVC to plasticized PVC or other materials such as leather, textiles, metals, paper, etc. in the shoe and furniture industry. The addition of a polyfunctional isocyanate to improves the heat-resistance and the strength of the joints.

General Information			
Features	Aroma		
Uses	Textile bonding		
	Metal bonding		
	Adhesive		
Appearance	White		
Forms	Particles		
Physical	Nominal Value	Unit	Test Method
Density (20°C)	1.19	g/cm <sup>3</sup>	ISO 2781
Viscosity <sup>1</sup> (20°C)	1.40 - 1.80	Pa · s	Internal method
Hydroxyl Value	0.10	%	Internal method
Activation temperature	50	°C	EN 12961
Additional Information	Nominal Value	Unit	Test Method
SOLUBILITY: Pearlstick® 46-10/16 is soluble in Methylene chloride, Acetone, Methyl Ethyl Ketone (MEK), Ethyl Acetate and Tetrahydrofuran (THF). Diluting solvents such as Toluene can be added in large amounts. The solvents and diluents should be water-free (max. 0.1 %), so as to avoid subsequent side reactions during crosslinking with isocyanate. It should be dissolved in closed tanks, and the use of a variable speed agitator is advisable. The final viscosity figures can vary, depending on the stirring process and on the solvent/diluents ratios			
NOTE			
1.	Brookfield RVF sp 4, 20 rpm. Solution at 15% in MEK		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT