

Lumid® HI1202A(W)

Polyamide 6
LG Chem Ltd.

Message:

Description
High Impact
Applications
Electric/Electronic Parts

General Information			
Features	High Impact Resistance		
Uses	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	1.4 to 1.8	%	ASTM D955
Water Absorption (Equilibrium)	1.1	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	46.1	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	40	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	1770	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 6.40 mm)	68.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.40 mm)	830	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.40 mm)	150	°C	ASTM D648
Peak Melting Temperature	220	°C	ASTM D3418
CLTE - Flow	1.1E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength (23°C, 1.00 mm)	20	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	2.80		ASTM D150
Arc Resistance ⁵	195	sec	ASTM D495
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	4.0 to 5.0	hr	
Rear Temperature	230 to 260	°C	
Middle Temperature	240 to 270	°C	

Front Temperature	250 to 280	°C
Nozzle Temperature	250 to 280	°C
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	60.0 to 80.0	°C
Back Pressure ⁶	0.490 to 1.96	MPa

NOTE

- | | |
|----|----------------|
| 1. | 50 mm/min |
| 2. | 50 mm/min |
| 3. | 2.8 mm/min |
| 4. | 2.8 mm/min |
| 5. | 23°C |
| 6. | Hydraulic Type |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

