

MAXAMID™ EPDMRC2066-HSL-BK09

Polyamide 66
Pier One Polymers, Inc.

Message:
MAXAMID™ EPDMRC2066HSL is available in black only with internal and external lubricants, UV and Heat stabilizer. Other modifications are available per request. Manufactured with recycled content. Further information and details are available upon request.

General Information			
Additive	Impact modifier		
	heat stabilizer		
	Lubricant		
	UV stabilizer		
Recycled Content	Yes		
Features	UV Stabilized		
	Impact modification		
	Thermal Stability		
	Lubrication		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	45.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	80	%	ASTM D638
Flexural Modulus (23°C)	1690	MPa	ASTM D790
Flexural Strength (23°C)	65.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	860	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	71.0	°C	ASTM D648
Peak Melting Temperature	255	°C	ASTM D3418
Injection	Nominal Value	Unit	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	290 - 305	°C	
Mold Temperature	65 - 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

