

SABIC® LDPE 2404AF00

Low Density Polyethylene
Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® LDPE 2404AF00 is a low density polyethylene product. It can be processed by extrusion coating and is available in Europe. SABIC® The application areas of LDPE 2404AF00 include food contact applications and coating applications. The main characteristics are: strong adhesion.

General Information			
Features	Low speed solidification crystal point		
	Good stripping		
	Good adhesion		
	Low shrinkage		
Uses	Coating application		
Agency Ratings	EEC 2002/72/EC		
	FDA 21 CFR 177.1520		
Forms	Particle		
Processing Method	Extrusion coating		
Physical	Nominal Value	Unit	Test Method
Density	0.925	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.2	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance ¹ (60°C, 2.00mm, molded)	3.00	hr	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/200
Yield, 1.60mm, molded	11.0	MPa	ISO 527-2/200
Fracture, 1.60mm, molded	14.0	MPa	ISO 527-2/200
Tensile Strain (fracture, 1.60mm, molded)	640	%	ISO 527-2/200
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	
Tensile Stress			ISO 527-3
MD: Yield, 25 µm	10.0	MPa	ISO 527-3
TD: Yield, 25 µm	9.00	MPa	ISO 527-3
MD : 25 µm	14.0	MPa	ISO 527-3
TD : 25 µm	13.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Break, 25 µm	300	%	ISO 527-3
TD: Break, 25 µm	450	%	ISO 527-3

Water Vapor Transmission Rate (38°C, 100% RH, 25 µm)	18	g/m ² /24 hr	Internal method
Oxygen Permeability (23°C, 25.0 µm) ²	0.80	cm ³ /cm ² /bar/24 hr	Internal method
Enthalpy Change	124	J/g	DIN 53765
Flexural Crack Resistance (25.0 µm)	2400	cycles/10 holes	Internal method
Tear Strength			ISO 6383-2
MD : 25.0 µm	12.0	kN/m	ISO 6383-2
TD : 25.0 µm	9.0	kN/m	ISO 6383-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	96.0	°C	ISO 306
Melting Temperature (DSC)	111	°C	DIN 53765
NOTE			
1.	2 MPa		
2.	0% RH		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT