

DOMAMID® 6ST1

Polyamide 6

DOMO Engineering Plastics SPA

Message:

Polyamide 6, improved impact resistance, for injection moulding.

General Information				
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.11	--	g/cm ³	ISO 1183
Molding Shrinkage ¹				ISO 2577
Across Flow : 23°C, 72 hr	1.4 to 1.6	--	%	
Flow : 23°C, 72 hr	1.1 to 1.3	--	%	
Water Absorption				ISO 62
Saturation, 23°C	8.8	--	%	
Equilibrium, 23°C, 50% RH	2.6	--	%	
Viscosity Number	145	--	cm ³ /g	ISO 307
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	110	--		ISO 2039-2
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2700	1000	MPa	ISO 527-2/1
Tensile Stress (Yield)	70.0	40.0	MPa	ISO 527-2/50
Tensile Strain (Break)	> 50	> 50	%	ISO 527-2/50
Flexural Modulus ²	2300	900	MPa	ISO 178
Flexural Stress ³	90.0	30.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	18	80	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Notched Izod Impact Strength (23°C)	15	75	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	No Break	No Break		ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	155	--	°C	ISO 75-2/B

1.8 MPa, Unannealed	60.0	--	°C	ISO 75-2/A
Vicat Softening Temperature	190	--	°C	ISO 306/B50
Melting Temperature	222	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	--	ohms	IEC 60093
Volume Resistivity	1.0E+15	--	ohms·cm	IEC 60093
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate	< 100	--	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	75.0 to 85.0		°C	
Drying Time	2.0 to 4.0		hr	
Processing (Melt) Temp	240 to 260		°C	
Mold Temperature	60.0 to 90.0		°C	
NOTE				
1.	50% RH			
2.	2.0 mm/min			
3.	2.0 mm/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

