

MarFlex® 5429

Low Density Polyethylene
Chevron Phillips Chemical Company LLC

Message:

MarFlex® 5429 is a low density polyethylene material. This product is available in North America or Latin America. The processing method is: cast film.
MarFlex® The main features of the 5429 are:
Antiblock software
slide
Transparency
Typical application areas include:
packing
Movie

General Information			
Additive	Anti-caking agent slip agent		
Features	Low density smoothness Anti-caking property Medium transparency		
Uses	Packaging Films		
Forms	Films		
Processing Method	cast film		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.2	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction	0.25		ASTM D1894
Films	Nominal Value	Unit	Test Method
Oxygen Permeability (32 µm)	170	cm ³ ·mm/m ² /atm/24 hr	ASTM D3985
Water Vapor Transmission	14	g/m ² /24 hr	ASTM E96
Dart Drop Test	29.0	kN/m	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	67.6	kN/m	ASTM D1922
TD	96.5	kN/m	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	98.3	°C	ASTM D1525
Melting Temperature	111	°C	DSC

Optical	Nominal Value	Unit	Test Method
Gloss (60°, 31.8 µm)	115		ASTM D2457
Haze (31.8 µm)	7.0	%	ASTM D1003
Additional Information			

Nominal Cast Film Properties at 1.25 milProcess Aid: NoneAntiblock: 10000Slip: 600

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

