

Delrin® 127UV NC010

ACETAL RESIN

DuPont Performance Polymers

Message:

UV Stabilized High Viscosity Acetal Homopolymer

General Information			
UL YellowCard	E41938-257622	E41938-101541287	
Additive	Lubricant		
	Mold Release		
	UV Stabilizer		
Features	Lubricated		
Uses	Profiles		
	Sheet		
Agency Ratings	UL Unspecified Rating		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
	Profile Extrusion		
	Sheet Extrusion		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Shear Stress vs. Shear Rate (ISO 11403-1)		
	Specific Volume vs Temperature (ISO 11403-2)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)	>POM<		
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.4	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	1.90	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.9	%	
Flow	2.1	%	

Water Absorption			
24 hr	0.50	%	ASTM D570
23°C, 24 hr, 2.00 mm	1.2	%	ISO 62
Equilibrium, 23°C, 2.00 mm, 50% RH	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ISO 2039-2
M-Scale	92		
R-Scale	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-2
Tensile Stress (Yield)	70.0	MPa	ISO 527-2
Tensile Strain (Yield)	23	%	ISO 527-2
Nominal Tensile Strain at Break	45	%	ISO 527-2
Flexural Modulus	2700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	11	kJ/m ²	
23°C	15	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	350	kJ/m ²	
23°C	400	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	11	kJ/m ²	
23°C	13	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	160	°C	ISO 75-2/B
1.8 MPa, Unannealed	93.0	°C	ISO 75-2/A
Vicat Softening Temperature	160	°C	ISO 306/B50
Melting Temperature ¹	178	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.2E-4	cm/cm/°C	
Transverse	1.1E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13	ohms · cm	IEC 60093
Relative Permittivity			IEC 60250
100 Hz	3.50		
1 MHz	3.40		
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (0.800 mm)	HB		IEC 60695-11-10, -20
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

