

TEKAMID™ TA210LW

Polyamide 66

Mando Advanced Materials Co., Ltd.

Message:

TA210LW is a unreinforced polyamide 66 product for low wear friction.

General Information			
Features	Low friction coefficient		
	Good wear resistance		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.5	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.2	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	83.4	MPa	ASTM D638
Tensile Elongation ² (Break)	65	%	ASTM D638
Flexural Modulus ³	2750	MPa	ASTM D790
Flexural Strength ⁴	108	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	235	°C	ASTM D648
1.8 MPa, not annealed	90.0	°C	ASTM D648
Peak Melting Temperature	260	°C	ASTM D3418
Flammability	Nominal Value	Test Method	
Flame Rating	V-2	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	4.0 - 5.0	hr	
Rear Temperature	250 - 270	°C	
Middle Temperature	260 - 280	°C	
Front Temperature	260 - 280	°C	
Nozzle Temperature	260 - 280	°C	
Processing (Melt) Temp	270 - 290	°C	
Mold Temperature	60.0 - 90.0	°C	
Injection instructions			
Injection Speed: 20 to 50%Injection Pressure - 1st: 30 to 60%Injection Pressure - 2nd: 30 to 60%Injection Pressure - Back Pressure: 0 to 20%			
NOTE			

1.	50 mm/min
2.	50 mm/min
3.	3.0 mm/min
4.	3.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

