

# Hanwha Total PP BJ522

Polypropylene Impact Copolymer  
HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:  
BJ522 is a high impact block copolymer which has high ethylene-propylene rubber content. Due to optimum rubber design, BJ522 has an excellent property balance between high stiffness and impact strength. BJ522 is a User Grade for automobile battery case and cover.

General Information			
Features	Block Copolymer		
	Rigidity, high		
	Impact resistance, high		
	Workability, good		
	Good heat sealability		
Uses	Battery box		
	Electrical appliances		
	Car interior parts		
	Automotive exterior parts		
	Container		
	Toys		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29.4	MPa	ASTM D638
Tensile Elongation (Break)	150	%	ASTM D638
Flexural Modulus	1320	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	49	J/m	ASTM D256
0°C	59	J/m	ASTM D256
20°C	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	110	°C	ASTM D648

Optical	Nominal Value	Test Method
Gloss	75	ASTM D2457

Injection	Nominal Value	Unit
Rear Temperature	170 - 200	°C
Middle Temperature	180 - 210	°C
Front Temperature	200 - 230	°C
Mold Temperature	30.0 - 50.0	°C
Injection Pressure	78.5 - 118	MPa
Holding Pressure	58.8 - 98.1	MPa

Injection instructions
------------------------

Cooling Time: 25 to 40 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

