

Hanwha Total PP TH54K

High Crystallinity Polypropylene
HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

TH54K is a super-heat-resistant polypropylene compound that exhibits significantly improved strength and heat-resistance due to the addition of the inorganic filler, talc to mo-polypropylene.

This product employs a variety of base PPs, such as HIPP (High Isotactic or High crystalline Polypropylene), and are manufactured with HANWHA TOTAL's special processing technology to ensure quality. Superior rigidity, long-term heat resistance, anti-static property, and dimensional stability are characteristic of these products. super-heat-resistant PP compound is widely used in electric and electronic products that are subject to high temperatures.

General Information			
UL YellowCard	E140331-222962		
Filler / Reinforcement	Talc		
Additive	Antistatic		
Features	Antistatic		
	Good Dimensional Stability		
	Good Processability		
	High Heat Resistance		
	High Rigidity		
	High Strength		
	Isophthalic		
Uses	Appliances		
	Electrical Parts		
	Electrical/Electronic Applications		
	Household Goods		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.15	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow (2.00 mm)	0.70 to 1.1	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	101		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	36.3	MPa	ASTM D638
Tensile Elongation ² (Break)	40	%	ASTM D638
Flexural Modulus ³	4120	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact (23°C)	34	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	147	°C	ASTM D648
Injection	Nominal Value	Unit	
Rear Temperature	180 to 200	°C	
Middle Temperature	190 to 210	°C	
Front Temperature	200 to 220	°C	
Mold Temperature	50.0 to 80.0	°C	
Injection Pressure	39.2 to 88.3	MPa	
Holding Pressure	58.8 to 98.1	MPa	
Screw Speed	30 to 80	rpm	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	5.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

