

Sorona® 3015GV NC010

RENEWABLY SOURCED™ THERMOPLASTIC POLYMER*

DuPont Performance Polymers

Message:

15% Glass Reinforced, Renewably Sourced, Polytrimethylene Terephthalate

General Information			
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Part Marking Code (ISO 11469)	>PTT-GF15<		
Resin ID (ISO 1043)	PTT-GF15		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Water Absorption (24 hr)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6500	MPa	ISO 527-2
Tensile Stress (Break)	125	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	5800	MPa	ISO 178
Flexural Stress	190	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.0	kJ/m ²	
23°C	5.5	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	30	kJ/m ²	
23°C	25	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	223	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Melting Temperature ¹	227	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.5E-5	cm/cm/°C	
Transverse	8.9E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Electric Strength	36	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.90		

1 MHz	3.70		
Dissipation Factor (100 Hz)	1.5E-3		IEC 60250
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.750 mm	HB		
1.50 mm	HB		
Oxygen Index	19	%	ISO 4589-2
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT