

Rotuba CA H2

Cellulose Acetate

Rotuba Extruders, Inc.

Message:

Rotuba CA H2 is a cellulose acetate (CA) product. It can be processed by injection molding and is available in North America. The application areas of Rotuba CA H2 include tools, consumer goods and medical/health care. The main features are: environmental protection/green.

General Information			
Features	Updatable resources		
	Good stability		
	Good color stability		
Uses	Mould		
	Buttons		
	Toys		
	Glasses		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Water Absorption (24 hr)	2.3	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	33.1	MPa	ASTM D638
Fracture	43.4	MPa	ASTM D638
Tensile Elongation (Yield)	35	%	ASTM D638
Flexural Modulus	1310	MPa	ASTM D790
Flexural Strength (Yield)	51.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	59	J/m	ASTM D256
23°C	190	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	66 - 77	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	216 - 232	°C	
Middle Temperature	216 - 232	°C	

Front Temperature	216 - 232	°C
Nozzle Temperature	221 - 232	°C
Mold Temperature	43 - 54	°C
Injection Pressure	8.27 - 11.0	MPa
Back Pressure	0.00 - 0.345	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT