

REXtac® APAO E-200

Polyalphaolefin
Huntsman Corporation

Message:
Modified Butene-1 copolymer

General Information			
Features		Copolymer amorphous Medium viscosity	
Uses		Adhesive	
Agency Ratings		FDA 21 CFR 175.105	
RoHS Compliance		Contact manufacturer	
Forms		Particle	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.880	g/cm ³	ASTM D792
Fill Analysis	Nominal Value	Unit	
Melt Density (190°C)	0.760	g/cm ³	
Additional Information			

Melt Viscosity, ASTM D3236, 275°F: 10500 cpsMelt Viscosity, ASTM D3236, 300°F: 6500 cpsMelt Viscosity, ASTM D3236, 325°F: 4200 cpsMelt Viscosity, ASTM D3236, 350°F: 3000 cpsMelt Viscosity, ASTM D3236, 375°F: 2000 cpsNeedle Penetration, ASTM D1321, 25°C: 2.0 mmSoftening Point by Ring and Ball, ASTM E28: 230°FOpen Time, Kraft/Kraft, Huntsman Method, 25°C: 300 secondsFlashpoint, COC, ASTM D93: >425°F

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

