

DIC.PPS Z-240

Polyphenylene Sulfide

DIC Corporation

Message:

Outline: Z-240 is a 40% glass fiber reinforced super tough PPS compound that provides excellent impact, thermal shock, and hot water resistance.
Color: Black

General Information			
UL YellowCard	E53829-101090628		
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	Good Impact Resistance		
	Good Thermal Shock Resistance		
	Low to No Water Absorption		
	Ultra High Toughness		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.61	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.25	%	
Across Flow	1.1	%	
Water Absorption (23°C, 24 hr)	0.030	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11500	MPa	ASTM D638
Tensile Strength	165	MPa	ASTM D638
Tensile Elongation (Break)	2.3	%	ASTM D638
Flexural Modulus	10500	MPa	ASTM D790
Flexural Strength	235	MPa	ASTM D790
Compressive Strength	180	MPa	ASTM D695
Poisson's Ratio	0.36		
Flexural Elongation at Break	3.0	%	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	130	J/m	ASTM D256
Unnotched Izod Impact	750	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	260	°C	ASTM D648
CLTE			ASTM D696
Flow : -30 to 100°C	2.0E-5	cm/cm/°C	
Transverse : -30 to 100°C	2.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (1.60 mm)	16	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	5.00		ASTM D150
Dissipation Factor (1 MHz)	5.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		Internal Method
Injection	Nominal Value	Unit	
Rear Temperature	290 to 320	°C	
Middle Temperature	290 to 320	°C	
Front Temperature	290 to 320	°C	
Mold Temperature	120 to 150	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

