

HiFill® POM CO GF/M30 UV BK

Acetal (POM) Copolymer
Techmer Engineered Solutions

Message:

HiFill® POM CO GF/M30 UV BK is an Acetal (POM) Copolymer product filled with 30% glass milled\glass fiber. It can be processed by injection molding and is available in North America.
Characteristics include:
Flame Rated
Chemically Coupled
Copolymer
UV Stabilized

General Information			
Filler / Reinforcement	Glass Milled\Glass Fiber,30% Filler by Weight		
Additive	UV Stabilizer		
Features	Chemically Coupled		
	Copolymer		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.63	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955
Water Absorption (24 hr)	0.25	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	84		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	96.5	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Flexural Strength	152	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	430	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	163	°C	
1.8 MPa, Unannealed	166	°C	
Melting Temperature	165	°C	
CLTE - Flow	3.8E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method

Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength ¹	20	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	71.1	°C	
Drying Time	1.0	hr	
Rear Temperature	177 to 193	°C	
Middle Temperature	188 to 210	°C	
Front Temperature	182 to 199	°C	
Nozzle Temperature	177 to 204	°C	
Processing (Melt) Temp	193 to 216	°C	
Mold Temperature	82.2 to 121	°C	

NOTE

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

