

Arnite® TV4 441

Polybutylene Terephthalate + PET
DSM Engineering Plastics

Message:

Arnite® TV4 441 is a Polybutylene Terephthalate + PET (PBT+PET) material filled with 20% glass fiber. It is available in Europe. Primary attribute of Arnite® TV4 441: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	1.2	%	
Flow	0.40	%	
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.15	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7300	MPa	ISO 527-2
Tensile Stress (Break)	112	MPa	ISO 527-2
Tensile Strain (Break)	2.7	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	7.0	kJ/m²	
23°C	7.0	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	25	kJ/m²	
23°C	25	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	200	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (1.60 mm)	HB		IEC 60695-11-10, -20
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 12	hr	
Rear Temperature	230 to 240	°C	
Middle Temperature	230 to 250	°C	

Front Temperature	240 to 260	°C
Nozzle Temperature	240 to 260	°C
Processing (Melt) Temp	240 to 270	°C
Mold Temperature	60.0 to 100	°C
Injection Rate	Moderate-Fast	
Back Pressure	3.00 to 10.0	MPa
Screw Compression Ratio	2.5:1.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

