

LNP™ STAT-KON™ AE004 compound

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

LNP STAT-KON* AE004 is a compound based on ABS resin containing 20% Carbon Fiber. Added feature of this material is: Electrically Conductive.

Also known as: LNP* STAT-KON* Compound AC-1004

Product reorder name: AE004

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 20% filler by weight		
Features	Conductivity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow: 24 hours	0.10 - 0.30	%	ASTM D955
Transverse flow: 24 hours	0.30 - 0.60	%	ASTM D955
Water Absorption			
24 hr, 50% RH	0.25	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.25	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	13000	MPa	ASTM D638
Tensile Strength			
Fracture ²	95.0	MPa	ASTM D638
Fracture	90.0	MPa	ISO 527-2/5
Tensile Elongation			
Fracture ³	2.6	%	ASTM D638
Fracture	2.3	%	ISO 527-2/5
Flexural Modulus			
50.0mm span ⁴	10600	MPa	ASTM D790
-- ⁵	12800	MPa	ISO 178
Flexural Stress			
--	152	MPa	ISO 178
Fracture, 50.0mm span ⁶	131	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	64	J/m	ASTM D256
23°C ⁷	6.4	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	320	J/m	ASTM D4812
23°C ⁸	16	kJ/m ²	ISO 180/1U

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, unannealed, 64.0mm span ⁹	105	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	213	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁰	101	°C	ISO 75-2/Af
Linear thermal expansion coefficient			ASTM D696
Flow: -30 to 30°C	2.0E-5	cm/cm/°C	ASTM D696
Lateral: -30 to 30°C	7.2E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 - 1.0E+4	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050 - 0.10	%	
Rear Temperature	204 - 216	°C	
Middle Temperature	232 - 243	°C	
Front Temperature	266 - 277	°C	
Processing (Melt) Temp	260	°C	
Mold Temperature	71.1 - 82.2	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	Type 1, 5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		
7.	80*10*4		
8.	80*10*4		
9.	80*10*4 mm		
10.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT