Witcom PE 2009/271

Polyethylene

Witcom Engineering Plastics B.V.

Message:

Witcom PE 2009/271 is a polyethylene product. It can be processed by injection molding and is available in Europe.

Features include

flame retardant/rated flame

Conductivity

General Information			
Features	Conductivity		
	Heat conduction		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm³	ISO 1183
Molding Shrinkage - Flow (3.00 mm)	0.60 - 1.0	%	ISO 2577
Water Absorption			ISO 62
Saturated, 23°C	0.020	%	ISO 62
Equilibrium, 23°C, 50% RH	0.010	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	< 45.0	МРа	ISO 527-2
Tensile Strain (Break)	2.0 - 4.0	%	ISO 527-2
Flexural Modulus	5500	MPa	ISO 178
Flexural Stress	45.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	2.8	kJ/m²	ISO 180/1A
Unnotched Izod Impact Strength	8.0	kJ/m²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Thermal Conductivity ¹	2.3	W/m/K	ASTM E1530
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 - 1.0E+4	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	НВ		ISO 1210
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Processing (Melt) Temp	180 - 240	°C	
Mold Temperature	20.0 - 60.0	°C	
Injection Rate	Fast		

Back Pressure 0.00 - 1.00 MPa

Injection instructions

Screw speed: 0.1 - 0.25 m/sInjection pressure: Keep to a minimumHold pressure: Keep to a minimum

NOTE

1. through plane

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

