

CP PRYME® Polypropylene PPC100/2I-20M NAT

Polypropylene Copolymer
Chase Plastics Services Inc.

Message:
Prime Polypropylene, 2 Izod, 20 Melt, Natural, FDA Compliant

General Information			
Features	Copolymer		
Agency Ratings	FDA not rated		
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.902	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	21.0	MPa	ASTM D638
Tensile Elongation (Yield)	10	%	ASTM D638
Flexural Modulus - Tangent	1000 - 1140	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Unnotched Izod Impact	1100	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	90.0	°C	ASTM D648
1.8 MPa, not annealed	50.0	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT