

DINALON® PA 6.6 MEDIO IMPACTO

Polyamide 66

Grupo Repol

Message:

DINALON®PA 6.6 MEDIO IMPACTO is a polyamide 66 (nylon 66) product. It can be processed by injection molding and is available in Europe.

- Features include:
- flame retardant/rated flame
 - Impact modification
 - Impact resistance

General Information			
Additive	Impact modifier		
Features	Impact modification		
	Medium impact resistance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm³	ASTM D792
Molding Shrinkage - Flow	2.8	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	70.0	MPa	ASTM D638
Tensile Elongation (Break)	20	%	ASTM D638
Flexural Modulus	2500	MPa	ASTM D790
Flexural Strength	75.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	95	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	200	°C	ASTM D1525
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
Additional Information			
Glow Wire, UNE 20-672-83: 650°C Vicat Softening Temperature, ASTM D1525: >200°C DTUL, ASTM D648: 75°C			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	275	°C	
Mold Temperature	80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

