

DURACON® NW-02LV

Acetal (POM) Copolymer + PE

Polyplastics Co., Ltd.

Message:

High sliding

General Information			
UL YellowCard	E45034-503345		
Features	Low VOC		
UL File Number	E45034		
Forms	Particle		
Processing Method	Injection molding		
Part Marking Code (ISO 11469)	>POM+PE		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	18.0	cm ³ /10min	ISO 1133
Water Absorption (23°C, 24 hr)	0.70	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2250	MPa	ISO 527-2
Tensile Stress	52.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	20	%	ISO 527-2
Flexural Modulus	2100	MPa	ISO 178
Flexural Stress	68.0	MPa	ISO 178
Coefficient of Friction			JIS K7218
Dynamic ¹	0.32		JIS K7218
With steel-dynamic ²	0.17		JIS K7218
Wear Factor			JIS K7218
0.98 MPa, 0.30 m/sec ³	< 1.0	10 ⁻⁸ mm ³ /N·m	JIS K7218
0.98 MPa, 0.30 m/sec ⁴	19	10 ⁻⁸ mm ³ /N·m	JIS K7218
0.060 MPa, 0.15 m/sec ⁵	400	10 ⁻⁸ mm ³ /N·m	JIS K7218
0.060 MPa, 0.15 m/sec ⁶	1000	10 ⁻⁸ mm ³ /N·m	JIS K7218
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.9	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	80.0	°C	ISO 75-2/A
Linear thermal expansion coefficient			Internal method
Flow: 23 to 55°C	1.2E-4	cm/cm/°C	Internal method

Lateral: 23 to 55°C	1.2E-4	cm/cm/°C	Internal method
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Additional Information	Nominal Value		
Color Number	CF2001/CD3501		
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	3.0 - 4.0	hr	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	60.0 - 80.0	°C	
Injection Pressure	49.0 - 98.0	MPa	
Screw Speed	100 - 150	rpm	
Injection instructions			
Injection speed: 5-50 mm/sInjection Holding pressure: Gate sealing time + alphaCooling: Plasticizing time or ejection capable time			
NOTE			
1.	vs. M90-44, 0.06 MPa, 15 cm/s		
2.	0.98 MPa, 30 cm/s		
3.	vs C-Steel, Steel Side		
4.	vs C-Steel, Material Side		
5.	vs M90-44, Material Side		
6.	vs M90-44, M90-44 Side		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT