

DINALON® B1S25 C15-4172

Polyamide 6

Grupo Repol

Message:

DINALON® B1S25 C15-4172 is a Polyamide 6 (Nylon 6) product filled with 15% carbon fiber. It is available in Europe. Primary characteristic: conductive.

General Information			
Filler / Reinforcement	Carbon Fiber, 15% Filler by Weight		
Features	Conductive		
Appearance	Black		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183
Humidity	< 0.25	%	ISO 15512/B
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11500	MPa	ISO 527-2/1
Tensile Stress (Yield)	160	MPa	ISO 527-2/5
Tensile Strain (Break)	1.8	%	ISO 527-2/5
Flexural Modulus ¹	8500	MPa	ISO 178
Flexural Stress ²	195	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	33	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	210	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	°C	ISO 306
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+3	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	245 to 275	°C	
Mold Temperature	60.0 to 90.0	°C	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT