

Durethan® BKV 40 H2.0 901510

Polyamide 6

LANXESS Asia/Pacific

Message:

PA 6, 40 % glass fibers, injection molding, heat-aging stabilized

General Information				
UL YellowCard		E245249-473597		
Filler / Reinforcement		Glass Fiber,40% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity				
--	1.46	--	g/cm ³	ASTM D792
23°C	1.46	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Across Flow : 280°C, 3.00 mm ¹	0.85	--	%	
Across Flow : 120°C, 4 hr, 3.00 mm ²	0.070	--	%	
Flow : 280°C, 3.00 mm ³	0.16	--	%	
Flow : 120°C, 4 hr, 3.00 mm ⁴	0.030	--	%	
Water Absorption				ISO 62
Saturation, 23°C	6.0	--	%	
Equilibrium, 23°C, 50% RH	1.8	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C ⁵	11800	7400	MPa	ASTM D638
23°C	11900	7800	MPa	ISO 527-2/1
Tensile Strength				
Break, 23°C	200	120	MPa	ASTM D638
Break, 23°C	195	130	MPa	ISO 527-2/5
Tensile Elongation				
Break, 23°C	3.0	4.0	%	ASTM D638
Break, 23°C	3.0	6.0	%	ISO 527-2/5
Flexural Modulus				
23°C	10800	6800	MPa	ASTM D790

23°C ⁶	11200	7300	MPa	ISO 178/A
Flexural Strength				
23°C	330	200	MPa	ASTM D790
3.5% Strain, 23°C	305	170	MPa	ISO 178/A
23°C ⁷	310	200	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁸ (23°C)	4.0	5.0	%	ISO 178/A
ISO Shortname	PA 6, GHR, 14-120, GF40	--		ISO 1874
Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	70	kJ/m ²	
23°C	85	90	kJ/m ²	
Notched Izod Impact				
-40°C, 3.18 mm	130	130	J/m	ASTM D256
23°C, 3.18 mm	160	190	J/m	ASTM D256
-30°C	13	11	kJ/m ²	ISO 180/1A
23°C	18	24	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed, 39.9 mm	215	--	°C	ASTM D648
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	--	°C	ISO 75-2/A
1.8 MPa, Annealed, 3.99 mm	200	--	°C	ASTM D648
Vicat Softening Temperature	> 200	--	°C	ISO 306/B120
Melting Temperature ⁹	222	--	°C	ISO 11357-3
RTI Elec (1.50 mm)	120	--	°C	UL 746
RTI Imp (1.50 mm)	95.0	--	°C	UL 746
RTI Str (1.50 mm)	140	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+10 to 1.0E+12	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+11 to 1.0E+12	ohms·cm	IEC 60093
Electric Strength				IEC 60243-1
23°C, 1.00 mm	40	35	kV/mm	
23°C, 3.00 mm	40	35	kV/mm	
Dielectric Constant				
23°C, 50 Hz ¹⁰	4.00	15.0		IEC 60250

23°C, 1 MHz ¹¹	4.00	5.00		IEC 60250
23°C, 100 Hz	4.00	10.0		IEC 60250
Dissipation Factor				IEC 60250
23°C, 50 Hz	0.010	--		
23°C, 100 Hz	5.0E-3	0.25		
	0.015	0.15		
23°C, 1 MHz	0.015	0.12		
Comparative Tracking Index				
Solution A	400	--	V	IEC 60112
--	--	375	V	ASTM D3638
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.50 mm	HB	--		
1.60 mm	HB	--		
3.00 mm	HB	--		
3.20 mm	HB	--		
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	270 to 290		°C	
Mold Temperature	80.0 to 120		°C	
NOTE				
1.	150x105x3mm, 80°C MT, 400 bar			
2.	150x105x3mm			
3.	150x105x3mm, 80°C MT, 400 bar			
4.	150x105x3mm			
5.	1.0 mm/min			
6.	2.0 mm/min			
7.	2.0 mm/min			
8.	2 mm/min			
9.	10°C/min			
10.	Tinfoil Electrodes			
11.	Tinfoil Electrodes			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

