

Luran® S 797SE

Acrylonitrile Styrene Acrylate
Styrolution

Message:

Luran S 797SE is suitable for extrusion applications. It provides the highest impact toughness within the product line.

General Information			
UL YellowCard	E108538-100840266		
Features	High Impact Resistance		
Uses	Automotive Applications		
	Sporting Goods		
Forms	Pellets		
Processing Method	Extrusion		
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)		
	Isochronous Stress vs. Strain (ISO 11403-1)		
	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm³	ISO 1183
Apparent Density ¹	0.59	g/cm³	
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	5.50	cm³/10min	ISO 1133
Molding Shrinkage	0.50 to 0.90	%	ISO 294-4
Water Absorption			ISO 62
Saturation, 23°C	1.7	%	
Equilibrium, 23°C, 50% RH	0.35	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	65.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	42.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	3.5	%	ISO 527-2
Tensile Creep Modulus (1000 hr)	1100	MPa	ISO 899-1
Flexural Stress	60.0	MPa	ISO 178
Films	Nominal Value	Unit	Test Method
Tensile Elongation - MD (Break)	11	%	
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength			ISO 179
-30°C	9.0	kJ/m ²	
23°C	40	kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-30°C	10	kJ/m ²	
23°C	30	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Annealed	100	°C	ISO 75-2/B
1.8 MPa, Annealed	95.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	104	°C	ISO 306/A50
--	90.0	°C	ISO 306/B50
CLTE - Flow	8.0E-5 to 1.1E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.17	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Dielectric Constant (100 Hz)	3.80		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	9.0E-3		
1 MHz	0.026		
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
NOTE			

1. With external lubricant

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

