

ColorRx® PC-1500NB

Polycarbonate
LTL Color Compounders, Inc.

Message:
A 15 melt Polycarbonate designed for use in medical equipment enclosures, such as monitoring and imaging devices, where body contact is not an issue.

General Information			
Uses	Medical/Healthcare Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	70		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	62.1	MPa	
Break	68.9	MPa	
Tensile Elongation			ASTM D638
Yield	7.0	%	
Break	130	%	
Flexural Modulus	2340	MPa	ASTM D790
Flexural Strength	96.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.35 mm)	129	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT